


	TPU-FC1
Day 0	3536
Day 0	4203
Day 0	4925
Day 90	1457
Day 90	1126
Day 90	1473
Day 200	151
Day 200	157
Day 200	96




	EVA
Day 0	4339
Day 0	5750
Day 0	4712
Day 90	4053
Day 90	4731
Day 90	4656
Day 200	4578
Day 200	4855
Day 200	3779

C)	Compo	st only	Replicate	
		1	2	3
	Day 0			
	Day 90			
	Day 200			

	compost only	
Day 0	51	
Day 0	23	
Day 0	81	
Day 90	7	
Day 90	68	
Day 90	6	
Day 200	9	
Day 200	19	
Day 200	5	

Supplemental Figure 1- Full scale images of all microplastic extraction filters. Tables to the left are particle counts of quantified microplastics generated in ImageJ. (A) Filters from TPU-FC1 at the indicated times/replicates. (B) Filters from the EVA samples at the indicated times/replicates. (C) Compost only control filters at the indicated times/replicates.



Supplemental Figure 2- Biodegradation of various prototype products made from bio-based TPU materials. (A) TPU-coated fabric after 2wk in compost conditions. (B) Control sample of TPU-coated fabric that was not exposed to compost after 2wk. (C) Injection molded TPU phone case after one year in compost. (D) Control images of TPU phone case not exposed to compost.